

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**



IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re PATENT APPLICATION OF
Inventors(s): Masakazu NISHIKAWA et al.

Group Art: 1773

Appln. No. 09/670,616

Examiner: BERNATZ, KEVIN M

Filed: September 27, 2000

Title: FLOPPY DISK


ACCURATE TRANSLATION OF PRIORITY DOCUMENT

RECEIVED
FEB 09 2004
TC 1700

The undersigned, of the below address, hereby states that he/she well knows both the English and Japanese languages, and that the attached is an accurate translation into the English language of the Certified Copy, filed for this application under 35 U.S.C. Section 119 and/or 365, of:

<u>Application No.</u>	<u>Country</u>	<u>Date Filed</u>
11-272644	Japan	September 27, 1999

Signed this 30th day of January, 2004

Signature: 

Name: AKIRA YONEZAWA

Address: 2-4, Nakahara 3-chome,

Higashi-yamato-shi,

TOKYO 207-0016 JAPAN

FF87/00Y

日本国特許庁
PATENT OFFICE
JAPANESE GOVERNMENT

別紙添付の書類に記載されている事項は下記の出願書類に記載されている事項と同一であることを証明する。

This is to certify that the annexed is a true copy of the following application as filed with this Office.

出願年月日

Date of Application:

1999年 9月27日

出願番号

Application Number:

平成11年特許願第272644号


出願人
Applicant(s):

富士写真フイルム株式会社

2000年 3月24日

特許庁長官
Commissioner,
Patent Office

近藤 隆彦



出証番号 出証特2000-3019525

PATENT OFFICE
JAPANESE GOVERNMENT

This is to certify that annexed is a true copy of the following
application as filed with this Office.

Date of Application : September 27, 1999

Application Number: 11-272644

Applicants : FUJ PHOTO FILM CO. LTD

March 24, 2000

Commissioner,
Patent Office Takahiko KONDO

The Number of Issue 2000-3019525

[NAME OF DOCUMENT] Patent Application

[REFERENCE NUMBER] FF826131Y

[FILING DATE] September 27, 1999

[ADDRESSEE] Commissioner, Patent Office Esq

[I P C] G11B 5/64

[INVENTOR] Masakazu NISHIKAWA
C/O FUJI PHOTO FILM Co., LTD., 12-1,
Ohgicho 2-chome, Odawara-shi, KANAGAWA

[INVENTOR] Makoto NAGAO
C/O FUJI PHOTO FILM Co., LTD., 12-1,
Ohgicho 2-chome, Odawara-shi, KANAGAWA

[APPLICANT] Identification Number : 000005201
FUJI PHOTO FILM Co., LTD.

[ATTORNEY] Identification Number : 100091971
Patent Attorney :
Akira YONEZAWA

[ATTORNEY] Identification Number : 100088041
Patent Attorney:
Ryukichi ABE

[ATTORNEY] Identification Number : 100092495
Patent Attorney:
Masanobu HIRUKAWA

[ATTORNEY] Identification Number : 100092509
Patent Attorney
Hiroki SHIRAI

[ATTORNEY] Identification Number : 100095120
Patent Attorney
Nobuhiko UCHIDA

[ATTORNEY] Identification Number : 100095980

Patent Attorney:

Hideo SUGAI

[ATTORNEY] Identification Number : 100094787

Patent Attorney:

Kenji AOKI

[ATTORNEY] Identification Number : 100097777

Patent Attorney:

Hiroshi NIRASAWA

[Priority Claim of Based on Patent Application]

Application Number: 11-367134

Application Date : December 24, 1998

[CHARGEABLE FEE] Register's Number for Pre-payment : 014845

Amount of payment : 21,000

[SUBMITTED DOCUMENTS] Name of Document : Specification 1

Name of Document : Abstract 1

THE NUMBER OF POWER OF ATTORNEY GENERAL : 9800695

[NECESSITY OF PROOF] YES

(NAME OF THE DOCUMENT) SPECIFICATION

(Title of the invention)

FLOPPY DISK

(SCOPE OF THE PATENT CLAIM)

- 5 1. A floppy disk, comprising a primer layer, a magnetic layer, a protective layer, and a lubricating layer coated on at least one of the surfaces of a flexible nonmagnetic support member, whereby a seed layer is provided between the flexible support member and the primer layer.
- 10 2. A floppy disk according to claim 1, wherein there is provided a flattening layer, comprising a heat-resistant polymer, on the flexible nonmagnetic support member.
3. A floppy disk according to claim 1 or 2, wherein thickness of the flattening layer is within the range of 0.1 -
15 5 μm .
4. A floppy disk according to any one of claims 1 to 3, wherein thickness of the flexible support member is within the range of 30 - 100 μm .
5. A floppy disk according to any one of claims 1 to 4,
20 wherein a Co-Cr alloy with Cr concentration within the range of 10 - 30 atom % is used for the magnetic layer.
6. A floppy disk according to any one of claims 1 to 5, wherein a Cr alloy with Cr concentration within the range of 77 - 100 atom % is used as the primer layer.
- 25 7. A floppy disk, comprising a flattening layer with thickness of 0.1 - 5 μm , a seed layer, a nonmagnetic primer layer containing Cr alloy with Cr concentration of 77 - 100 atom %, a magnetic layer containing Co-Cr alloy with Cr

concentration of 10 - 30 atom %, a protective layer, and a lubricating layer, all of said layers being coated on at least one of the surfaces of a flexible support member with thickness of 30 - 100 μ m, whereby thickness of the seed layer is 5 - 100 nm, and linear expansion coefficient (E_{SE}) of the metal seed layer and linear expansion coefficient (E_{UL}) of the nonmagnetic primer layer satisfy the relation: $|E_{SE} - E_{UL}|/E_{UL} < 0.3$, and tensile strength (S_{SE}) of the metal seed layer and tensile strength (S_{UL}) of the nonmagnetic primer layer satisfy the relation: $S_{SE}/S_{UL} > 1$.

(DETAILED DESCRIPTION OF THE INVENTION)

(TECHNICAL FIELDS TO WHICH THE INVENTION BELONGS)

The present invention relates to a magnetic recording medium with high recording density, and in particular, to a removable type magnetic recording medium to be used in auxiliary memory unit, image storage unit, etc. of a computer. Further, the invention relates to a floppy disk using a flexible support member with high recording density of 1 GB or more per square inch.

(Description of the Prior Art)

With extreme increase in the capacity of electronic data prepared in devices such as personal computer, there are now strong demands on the development of a removable type disk comprising high capacity magnetic recording medium for the purpose of storing large amount of electronic data and for backup operation.

Up to now, digital video tape has been primarily used as ultra-high density recording medium for business use. With

rapid increase in the amount of information in recent years,
there are now demands on technical development to seek higher
capacity and higher speed for recording and reproduction.

Instead of the video tape currently used as main stream in this
5 field, attempts are now being made to use removable type disk
with better recording and reproducing speed as a digital
recording medium for business use.

On the other hand, in the high density magnetic recording
medium of GB class currently in use, a disk made of aluminum,
10 glass, etc., i.e. the so-called hard disk, is used. When shock
is applied on the device, head crash may occur, and both medium
and head may be subjected to serious damage. This problem of
shock-resistant property is not yet overcome in the removable
type hard disk, and this has hindered the use as recording
15 means in portable devices such as digital disk camera.

When the support member is changed from hard disk to a
flexible member of the same type as a floppy disk, it is
advantageous in that the recording unit can be produced in
lightweight design, and damage at head crash can be alleviated.
20 In this respect, there are now strong demands on the
development of high density removable type magnetic recording
medium using a flexible support member with high shock-
resistant property as substrate.

In a removable type magnetic recording medium, a magnetic
25 layer comprising a ferromagnetic metal or alloy is formed on a
substrate. In particular, in the high density magnetic
recording medium, for a ferromagnetic layer formed on the
magnetic recording medium, a magnetic layer is formed by vacuum

film forming method.

However, in the removable type magnetic recording medium using a flexible support member, there have been problems in that cracking occurs during manufacturing process and the
5 product cannot be used as a medium.

(Problems to be solved by the Invention)

It is an object of the present invention to provide a floppy disk type magnetic recording medium with high quality in a removable type high density magnetic recording medium using a
10 flexible support member as substrate, and to prevent cracking in the manufacturing process.

(Means for Overcoming the Problems)

The above problems can be solved by a floppy disk, which comprises a primer layer, a magnetic layer, a protective layer,
15 and a lubricating layer coated on at least one of the surfaces of a flexible nonmagnetic support member, whereby a seed layer is provided between the flexible support member and the primer layer.

Also, the present invention provides a floppy disk as
20 described above, wherein there is provided a flattening layer with thickness of $0.1 - 5 \mu\text{m}$.

Further, the present invention provides a floppy disk as described above, wherein thickness of the flexible support member is within the range of $30 - 100 \mu\text{m}$.

25 Also, the present invention provides a floppy disk as described above, wherein a Co-Cr alloy with Cr concentration within the range of $10 - 30 \text{ atom } \%$ is used for the magnetic layer.

Further, the present invention provides a floppy disk as described above, wherein a Cr alloy with Cr concentration within the range of 77 - 100 atom % is used as the primer layer.

Also, the present invention provides a floppy disk, which
5 comprises a flattening layer with thickness of 0.1 - 5 μm , a seed layer, a nonmagnetic primer layer containing Cr alloy with Cr concentration of 77 - 100 atom %, a magnetic layer containing Co-Cr alloy with Cr concentration of 10 - 30 atom %, a protective layer, and a lubricating layer, all of said layers
10 being coated on at least one of the surfaces of a flexible support member with thickness of 30 - 100 μm , whereby thickness of the seed layer is 5 - 100 nm, and linear expansion coefficient (E_{SE}) of the metal seed layer and linear expansion coefficient (E_{UL}) of the nonmagnetic primer layer satisfy the
15 relation: $|E_{\text{SE}} - E_{\text{UL}}|/E_{\text{UL}} < 0.3$, and tensile strength (S_{SE}) of the metal seed layer and tensile strength (S_{UL}) of the nonmagnetic primer layer satisfy the relation: $S_{\text{SE}}/S_{\text{UL}} > 1$.

(Embodiment for Carrying Out of the Invention)

20 The present inventors have found that it is possible to provide a floppy disk with stable performance characteristics. Specifically, on at least one of the surfaces of a flexible nonmagnetic support member, a primer layer, a magnetic layer, a protective layer, and a lubricating layer are coated to obtain
25 a floppy disk. By providing a seed layer between the flexible support member and the primer layer, it is possible to prevent cracking in the manufacturing process and to obtain a floppy disk with stable performance characteristics.

Further, a specific type of flattening layer, a primer layer and a magnetic layer are formed on the nonmagnetic support member. Also, the following material is used as seed layer, i.e. linear expansion coefficient (E_{SE}) of the metal seed layer and linear expansion coefficient (E_{UL}) of the nonmagnetic primer layer satisfy the relation: $|E_{SE} - E_{UL}|/E_{UL} < 0.3$, and tensile strength (S_{SE}) of the metal seed layer and tensile strength (S_{UL}) of the nonmagnetic primer layer satisfy the relation: $S_{SE}/S_{UL} > 1$. As a result, it was found that cracking can be prevented when the medium is prepared.

Specifically, cracking often occurs on the ferromagnetic metal thin film formed on a substrate using a flexible material as the nonmagnetic support member. It was found that this is caused by flatness which is required on a magnetic recording medium with high recording density and also by thermal expansion of the seed layer, the primer layer, etc. formed on the magnetic recording medium.

When a hard disk made of aluminum, glass, etc. is used as a support member, it is possible to attain flatness closer to mirror surface by polishing. In case of a floppy disk, however, a flexible support member is used as the support member, and it is very difficult to improve the flatness by polishing. In this respect, by providing a flattening layer made of polymer on the flexible support member, the surface property similar to a hard disk support member can be attained. On the flattening layer, a nonmagnetic primer layer and a magnetic layer are formed by sputtering. In order to increase magnetostatic property and electromagnetic transfer characteristics of the magnetic layer,

it is necessary to heat the support member at high temperature of 100°C - 300°C. Or, temperature of the support member is effectively increased when bias voltage application, RF sputtering method, etc. are used.

5 The medium with the nonmagnetic primer layer and the magnetic layer formed on it is cooled down to room temperature and is taken out of a sputtering device. During the manufacturing process with varying temperature, the flexible support member, the flattening layer, the nonmagnetic primer
10 layer, and the magnetic layer are subject to thermal expansion and shrinking.

 In a hard disk, the support member is made of hard material, and metal, ceramics, glass, etc. are used as the material. In this respect, difference of expansion coefficient is small
15 between the primer layer and the support member, and there is less possibility that cracking occurs during heating and cooling processes due to the difference in thermal expansion. In a magnetic recording medium using a flexible support member as substrate, the flexible support member and the flattening
20 layer are made of macromolecular compositions, and the nonmagnetic primer layer and the magnetic layer are made of metal material. For this reason, thermal expansion or shrinking differs between these two layers by about one digit. The material of the nonmagnetic primer layer cannot endure the
25 deformation of the support member when cooled down, and this may result in cracking on the magnetic recording medium.

 When a nonmagnetic primer layer, i.e. a seed layer, is provided between the flattening layer and the primer layer, a

force generated between the flattening layer and the primer layer which occurs when the support member is cooled down is received by the primer layer and the seed layer. As a result, film strength is improved, and cracking can be prevented.

5 It is proposed to use the following material as the material of the seed layer and the primer layer, i.e. a material, in which linear expansion coefficient (E_{SE}) of the metal seed layer and linear expansion coefficient (E_{UL}) of the nonmagnetic primer layer satisfy the relation: $|E_{SE} - E_{UL}|/E_{UL} <$
10 0.3, and tensile strength (S_{SE}) of the metal seed layer and tensile strength (S_{UL}) of the nonmagnetic primer layer satisfy the relation: $S_{SE}/S_{UL} > 1$. Then, it is possible to cope with the force, which is generated due to the difference of linear expansion coefficient between the primer layer and the magnetic
15 layer in the cooling process, and cracking can be prevented on higher level.

Specifically, the invention provides a floppy disk with ultra-high recording density, which comprises at least a primer layer, a magnetic layer, a protective layer, and a lubricating
20 layer on a flexible support member, and by which it is possible to prevent cracking during the preparation of the medium.

For the purpose of preventing cracking during the above process, such materials are used that linear expansion coefficient (E_{SE}) of the metal seed layer and linear expansion
25 coefficient (E_{UL}) of the nonmagnetic primer layer satisfy the relation: $|E_{SE} - E_{UL}|/E_{UL} < 0.3$, and tensile strength (S_{SE}) of the metal seed layer and tensile strength (S_{UL}) of the nonmagnetic primer layer satisfy the relation: $S_{SE}/S_{UL} > 1$. As

a result, it is possible to prevent cracking during the preparation of the medium and to provide a floppy disk with high recording density.

Next, description will be given on the materials which are preferably used in the present invention.

As the support member of the magnetic recording medium of the present invention, polyethylene terephthalate, polyethylene naphthalate, polyimide, polyamide, polyamideimide, polybenzoxazole, etc. may be used. Young's modulus of the support member of the magnetic recording medium of the present invention is preferably 200 - 1600 kg/mm², or more preferably 300 - 800 kg/mm². The thickness of the support member is preferably 20 - 150 μ m, or more preferably 30 - 80 μ m.

To improve the flatness of the surface of the support member, a flattening layer is provided on the support member. For the flattening layer, heat-resistant polymer may be extensively used. More preferably, the material such as silicone resin, polyamide resin, polyamideimide resin, polyimide resin, etc. may be used. These materials have high heat-resistant property and exhibit excellent performance in surface property and magnetostatic property. Coating thickness of the flattening layer is preferably 0.1 - 5.0 μ m, or more preferably 0.5 - 3.0 μ m, or most preferably 0.8 - 2.0 μ m.

Micro-size projections, e.g. fine particles of inorganic substances such as SiO₂, Al₂O₃, TiO₂, etc. or fine particles of organic substances, may be provided on the surface of the flattening layer. Particle size of the fine particles to be used for the formation of micro-size projections is preferably

5 - 40 nm, or more preferably 10 - 35 nm, or most preferably 15 - 30 nm. The height of the projection to be formed on the surface of the flattening layer is preferably 30 nm or less.

When particle size of the fine particles to be formed on the surface of the flattening layer is less than 5 nm, the effect of the presence of fine particles on the surface of the flattening layer cannot be attained. If it is more than 40 nm, surface irregularities may occur on the layer subsequently formed, and this may lead to lower flatness.

10 The seed layer to be formed between the flattening layer and the primer layer, preferably contains at least one type of metal of Ta, Mo, W, V, Zr, Cr, Rh, Hf, Nb, Mn, Ni, Al, Ru, Ti and Si, or an alloy containing two types or more of these elements. Also, the material may contain oxygen, nitrogen, etc.

15 The thickness of the seed layer is preferably 10 - 100 nm, or more preferably 15 - 80 nm, or most preferably 20 - 60 nm. If the seed layer is thinner than 10 nm, the structure of the seed layer may become discontinuous. A force generated due to thermal shrinking may be applied on the primer layer, and cracking may occur. If it is thicker than 100 nm, cracking and film detachment may occur on the magnetic recording medium due to film stress on the seed layer. The seed layer can be produced by DC sputtering under argon atmosphere. The temperature suitable for producing the seed layer is 5°C - 250°C, 20 or more preferably 10°C - 200°C.

As the material for the nonmagnetic primer layer, it is preferable to use chromium or an alloy containing chromium and at least one type of metals of Ti, W, Mo, V, Ta, B, Si, Nb, Zr,

Al and Mn. Cr concentration of the nonmagnetic primer layer is 77 - 100 atom %, or more preferably 80 - 95 atom %, and the remainder is metals of the other elements.

The thickness of the nonmagnetic primer layer is preferably
5 5 - 500 nm, or more preferably 10 - 100 nm. If the primer layer is thicker than 500 nm, particle size of the magnetic layer is increased, and this leads to the increase of medium noise.

It is necessary to design in such manner that linear expansion coefficient (E_{SE}) of the metal seed layer and linear
10 expansion coefficient (E_{UL}) of the nonmagnetic primer layer satisfy the relation: $|E_{SE} - E_{UL}|/E_{UL} < 0.3$, and tensile strength (S_{SE}) of the seed layer and tensile strength (S_{UL}) of the nonmagnetic primer layer satisfy the relation: $S_{SE}/S_{UL} > 1$. More preferably, the following relations must be satisfied:

15 $|E_{SE} - E_{UL}|/E_{UL} < 0.2$ and
 $S_{SE}/S_{UL} > 1.1$

As the material for the medium to satisfy the above relations, Ta (film thickness: 20 nm; input power: 11.4 W/cm²; argon partial pressure: 8 mTorr) may be used as the material
20 for the seed layer, and CrTi₂₀ (film thickness: 60 nm; input power 11.4 W/cm²; argon partial pressure: 15 mTorr) may be used as the material for the nonmagnetic primer layer.

As the magnetic material to form the magnetic layer, cobalt-chromium alloy may be preferably used. In particular, it
25 is preferable to use cobalt-chromium alloy containing Pt, Ta, Ni, Si, B, Ni, or Pd. Also, oxygen may be contained.

Among these materials, it is more preferable to use Co-Cr-Pt or Co-Cr-Pt-Ta because these have superb property in both

output and noise characteristics. In addition to cobalt-chromium alloy, barium ferrite may be used. Cr concentration in the ferromagnetic layer is preferably 10 - 30 atom %, or more preferably 12 - 28 atom %, or most preferably 15 - 25 atom %.

5 Film thickness of the magnetic layer is preferably 10 - 300 nm, or more preferably 10 - 60 nm.

It is preferable that the nonmagnetic primer layer and the magnetic layer are formed by vacuum film forming method. In particular, it is preferable to use the sputtering method
10 because film can be formed without changing composition of the elements. Also, it is preferable to continuously form the film under vacuum condition for all of the seed layer, the primer layer and the magnetic layer.

It is preferable to provide a carbon film comprising
15 amorphous carbon, graphite, diamond structure or mixture of these materials prepared by plasma CVD method, sputtering method, etc. on the magnetic layer as a protective layer. In particular, it is preferable to use hard amorphous carbon film, generally called diamond-like carbon. This hard carbon film is
20 preferably 1000 kg/mm² or more in Vickers hardness, or more preferably 2000 kg/mm².

The film thickness of the protective layer is preferably 2.5 - 30 nm, or more preferably 5 - 25 nm.

In the magnetic recording medium of the present invention,
25 with the purpose of improving running durability and corrosion-resistant property, it is preferable to add lubricant or rust-preventive agent on the magnetic layer or the protective layer.

As the lubricant, hydrocarbon type lubricant, fluorine type

lubricant, extreme-pressure additive, etc. already known in the art may be used. As the hydrocarbon type lubricant, carboxylic acids such as stearic acid, oleic acid, etc., esters such as butyl stearate, sulfonic acids such as octadecyl sulfonic acid, 5 phosphoric acid esters such as monooctadecyl phosphate, alcohols such as stearyl alcohol, oleyl alcohol, etc., carboxylic acid amide such as stearic acid amide, etc., amines such as stearyl amine may be used.

As the fluorine type lubricant, a lubricant prepared by 10 substituting a part or all of the alkyl groups in the hydrocarbon type lubricant by fluoroalkyl group or perfluoropolyether group may be used. As the perfluoro-polyether group, perfluoromethylene oxide polymer, perfluoroethylene oxide polymer, perfluoro-n-propylene oxide 15 polymer $(CF_2CF_2CF_2O)_n$, perfluoroisopropylene oxide polymer $(CF(CF_3)CF_2O)_n$ or copolymer of these compounds may be used.

As the extreme-pressure additive, phosphoric acid esters such as trilauryl phosphate, phosphorous acid esters such as trilauryl phosphite, thiophosphorous acid esters such as 20 trilauryl trithiophosphite, sulfur type extreme-pressure agent such as dibenzyl disulfide may be used.

The lubricants as described above may be used alone or in combination. To apply these lubricants on the protective layer, the lubricant is dissolved in an organic solvent, and it is 25 coated by wire bar method, gravure method, spin coat method, dip coat method, etc., or it may be attached by vacuum evaporation method.

The coating quantity of the lubricant is preferably 1 - 30

mg/m², or more preferably, 2 - 20 mg/m².

As the rust-preventive agent to be used in the present invention, nitrogen-containing heterocyclic compounds such as benzotriazole, benzimidazole, purine, pyrimidine, etc.,
5 derivatives prepared by introducing alkyl side-chain to or the base nucleus, nitrogen- or sulfur-containing hetero-cyclic compounds and derivatives such as benzothiazole, 2-mercaptobenzothiazole, tetrazaindene cyclic compound, thiouracil compound may be used

10 [Examples]

In the following, description will be given on examples and comparative examples to explain the features of present invention:

(Example 1)

15 On a polyimide flexible support member of 75 μ m in thickness, polyimide resin of 1 μ m in thickness was provided as a flattening layer. Tantalum was coated on it in thickness of 20 nm as a seed layer by DC sputtering method under the conditions of argon partial pressure of 8 mTorr, input power of
20 11.4 W/cm², and support member temperature of 20°C. Further, as the nonmagnetic primer layer, chromium alloy containing titanium by 20 atom % was coated in thickness of 60 nm by DC sputtering method under the conditions of argon partial pressure of 15 mTorr, input power of 11.4 W/cm², and support
25 member temperature of 200°C.

Next, as the magnetic layer, a Co alloy thin film containing Cr by 20 atom % and Pt by 12 atom % was formed by DC sputtering method on the nonmagnetic primer layer under the

conditions of argon partial pressure of 1.5 mTorr, input power of 11.4 W/cm², support member temperature of 200°C, and film thickness of 30 nm.

Next, on the magnetic layer, a carbon protective layer of 20 nm in thickness was formed by DC sputtering method under the conditions of argon partial pressure of 3 mTorr, and input power of 5.71 W/cm².

Further, monolauryl phosphate (CH₃(CH₂)₁₁OPO₃H₂) and amine stearate (CH₃(CH₂)₁₇NH₂) were dissolved in methanol, and this solution was coated as lubricant by wire bar method in such manner that molar ratio of organic acid and amine will be 1:1 and coating amount of these two substances will be 6 mg/m², and a floppy disk was prepared.

(Examples 2 to 6)

A floppy disk was prepared for each of Examples 2 to 12 by the same procedure as in Example 1 except that the material for the seed layer or the material for the nonmagnetic primer layer in Example 1 was changed to the material shown in Table 1.

(Comparative example 1)

A floppy disk of Comparative example 1 was prepared by the same procedure as in Example 1 except that the seed layer was not provided.

(Comparative examples 2 to 11)

A floppy disk for each of Comparative examples 2 to 11 was prepared by the same procedure as in Example 1 except that the material for the seed layer in Example 1 was changed to the material shown in Table 1.

Each magnetic recording medium in the Examples and

Comparative examples as described above was measured by the measuring methods given below. The results of the measurement are shown in Table 1.

(Measuring methods)

5 (1) Linear expansion coefficient

For the measurement of linear expansion coefficient, a sputtering device (S-50S; Shibaura Engineering Works Co., Ltd.) was used. The specimen was heated to 300°C using a lamp heater under vacuum condition of 10^{-6} Torr or lower. The amount of
10 deformation of the specimen was obtained using a strain gauge (strain gauge WK; Micromasurement Inc.) mounted on both surfaces of the specimen.

A specimen of 5 mm × 30 mm with a single layer formed on each of both surfaces of a polyimide support member was used.
15 To exclude the influence of deformation of the support member, the strain gauge was also mounted on the support member using polyimide only, and the amount of deformation was measured on each of the specimens.

The amount of deformation (V_{sp}) of the specimen with the
20 film formed on it and the amount of deformation (V_{pi}) of the support member using polyimide only were measured. A difference of the amount of deformation between these two, i.e. ($V_{sp} - V_{pi}$), was defined as the amount of deformation of the formed film. Linear expansion coefficient was obtained by the
25 following equation:

Linear expansion coefficient

$$= (V_{sp} - V_{pi}) / \text{length of specimen} / \text{temperature difference}$$

(2) Tensile strength

Under the conditions given in Examples and Comparative examples, a single layer was formed on each of both surfaces of the polyimide support member. This specimen in size of 5 mm × 30 mm was pulled using a tensile tester (Tensilon STM-T-50BP; Tokyo Boring Co., Ltd.). The surface of the formed film was examined under microscope with magnifying factor of 200 x, and a value of load, under which cracking occurred, was defined at tensile strength.

(3) Cracking

A protective layer was formed by sputtering method. After cooling down, the surface of the specimen was examined under differential interference type microscope (XP(U)NR-A; Nikon Corporation). The specimen was examined at 30 points at random with magnifying factor of 200 x. When no cracking was found during 30 measurements, it was defined as "very good". If cracks were found at 2 points or less, it was defined as "good". If cracks were found at more than 2 points, it was regarded as "no good".

Table 1

	Primer layer	E _{UL}	S _{UL}	Seed layer	E _{SL}	S _{SL}	Expansion ratio	Strength ratio	Cracks
Example 1	CrTi ₂₀	6.9	38.4	Ta	6.5	53.0	0.13	1.38	Very good
Example 2	CrTi ₂₀	6.9	38.4	Mo	5.1	49.0	0.26	1.28	Very good
Example 3	CrTi ₂₀	6.9	38.4	Rh	8.5	54.9	0.23	1.43	Very good
Example 4	CrMo ₂₀	6.2	43.0	Ta	6.5	53.0	0.04	1.23	Very good
Example 5	CrMo ₂₀	6.2	43.0	Mo	5.1	49.0	0.18	1.13	Very

									good
Example 6	CrTi ₂₀	6.9	38.4	CrTi ₂₅	6.3	39.2	0.09	1.00	Good
Example 7	CrTi ₂₀	6.9	38.4	Zr	5.0	35.0	0.27	0.91	Good
Example 8	CrTi ₂₀	6.9	38.4	Nb	7.2	21.0	0.04	0.73	Good
Example 9	CrTi ₂₀	6.9	38.4	Ir	6.8	20.3	0.01	0.53	Good
Example 10	CrTi ₂₀	6.9	38.4	Mn	23.0	50.4	2.33	1.31	Good
Example 11	CrTi ₂₀	6.9	38.4	Al	23.5	4.76	2.41	0.13	Good
Example 12	CrMo ₂₀	6.2	43.0	Rh	8.5	54.9	0.37	1.27	Good
Comparative example 1	CrTi ₂₀	6.9	38.4	-	-	-	-	-	No good
Comparative example 2	CrMo ₂₀	5.8	43.0	-	-	-	-	-	No good
Comparative example 3	Cr	6.2	42.0	-	-	-	-	-	No good
Comparative example 4	Rh	8.5	54.9	-	-	-	-	-	No good
Comparative example 5	Zr	5.0	35.0	-	-	-	-	-	No good
Comparative example 6	Ta	6.5	53.0	-	-	-	-	-	No good
Comparative example 7	Mo	5.1	49.0	-	-	-	-	-	No good
Comparative example 8	Mn	23.0	50.4	-	-	-	-	-	No good
Comparative example 9	Al	23.5	4.76	-	-	-	-	-	No good
Comparative example 10	Mo	5.1	49.0	-	-	-	-	-	No good
Comparative example 11	CrTi ₂₀	6.3	39.2	-	-	-	-	-	No good

In Table 1,

E_{UL} : Linear expansion coefficient of the primer layer
(unit: 10^{-6})

5 S_{UL} : Tensile strength of the primer layer
(unit: kg/mm^2)

E_{SE} : Linear expansion coefficient of the seed layer
(unit: 10^{-6})

10 S_{SE} : Tensile strength of the seed layer
(unit: kg/mm^2)

Expansion ratio: $|E_{SE} - E_{UL}|/E_{UL}$

Strength ratio: S_{SE}/S_{UL}

(Effects of the Inventions)

As described above, a flattening layer is formed on a
5 flexible support member, and a seed layer is provided between
the above layer and a nonmagnetic primer layer which is formed
as a primer layer of the magnetic layer, and linear expansion
coefficient and tensile strength of the seed layer and the
nonmagnetic primer layer were set to specific values. As a
10 result, film strength is increased, and it is possible to
prevent cracking due to thermal expansion which occurs when the
magnetic recording medium is exposed to temperature increase or
cooling during manufacturing process, and the magnetic
recording medium for high density recording can be manufactured
15 in stable manner.

(DOCUMENT NAME) ABSTRACT

(Abstract)

(Problems to be Solved)

To prevent the occurrence of cracks in the production of
5 a floppy disk having a high recording density.

(Solutions)

In a magnetic recording medium, which comprises a
flattening layer with thickness of $0.1 - 5.0 \mu\text{m}$, a seed layer,
a nonmagnetic primer layer containing chromium with chromium
10 concentration of $77 - 100 \text{ atom } \%$, a Co-Cr type alloy magnetic
layer, a protective layer, and a lubricating layer coated
sequentially on at least one of the surfaces of a flexible
nonmagnetic support member, whereby the metal seed layer is
designed in such manner that linear expansion coefficient (E_{SE})
15 of the metal seed layer and linear expansion coefficient (E_{UL})
of the nonmagnetic primer layer satisfy the relation: $|E_{SE} - E_{UL}|$
 $|E_{UL}| < 0.3$, and tensile strength (S_{SE}) of the metal seed layer
and tensile strength (S_{UL}) of the nonmagnetic primer layer
satisfy the relation: $S_{SE}/S_{UL} > 1$, and a floppy disk is produced
20 by preventing cracking during the manufacture of the floppy
disk.